

SERTLİK TABLOSU

Çekme Dayanımı (Mpa)	Brinell Sertliği (BHN)	Vickers Sertliği (HV)	Rockwell Sertliği (HRB)	Rockwell Sertliği (HRC)
285	86	90	-	-
320	95	100	56.2	-
350	105	110	62.3	-
385	114	120	66.7	-
415	124	130	71.2	-
450	133	140	75.0	-
480	143	150	78.7	-
510	152	160	81.7	-
545	162	170	85.0	-
575	171	180	87.1	-
610	181	190	89.5	-
640	190	200	91.5	-
675	199	210	93.5	-
705	209	220	95.0	-
740	219	230	96.7	-
770	228	240	98.1	-
800	238	250	99.5	-
820	242	255	-	23.1
850	252	265	-	24.8
880	261	275	-	26.4
900	266	280	-	27.1
930	276	290	-	28.5
950	280	295	-	29.2
995	295	310	-	31.0
1030	304	320	-	32.2
1060	314	330	-	33.3
1095	323	340	-	34.4
1125	333	350	-	35.5
1155	342	360	-	36.6
1190	352	370	-	37.7
1220	361	380	-	38.8
1255	371	390	-	39.8
1290	380	400	-	40.8
1320	390	410	-	41.8
1350	399	420	-	42.7
1385	409	430	-	43.6
1420	418	440	-	44.5
1455	428	450	-	45.3
1485	437	460	-	46.1
1520	447	470	-	46.9
1555	456	480	-	47.7
1595	466	490	-	48.4
1630	475	500	-	49.1
1665	485	510	-	49.8
1700	494	520	-	50.5
1740	504	530	-	51.1
1775	513	540	-	51.7
1810	523	550	-	52.3
1845	532	560	-	53.0
1880	542	570	-	53.6
1920	551	580	-	54.1
1955	561	590	-	54.7
1995	570	600	-	55.2
2030	580	610	-	55.7
2070	589	620	-	56.3
2105	599	630	-	56.8
2145	608	640	-	57.3
2180	618	650	-	57.8